

## Standard Aluminium Sashless in Capral 400 Frame – Single Glazed

Window ID	Glazing	Heat%	Cool %	Uw	SHGC	Tvw	Air Inf
AVW-003-01	6Clr	16%	23%	6.2	0.63	0.65	1.83
AVW-003-02	6Gy	8%	37%	6.2	0.45	0.31	1.83
AVW-003-03	6SpGy	0,01%	49%	6.2	0.28	0.06	1.83
AVW-003-04	6EV	28%	41%	4.8	0.49	0.50	1.83
AVW-003-05	6ET	33%	39%	4.6	0.53	0.60	1.83
AVW-003-06	6.38Sx	17%	25%	6.1	0.61	0.65	1.83
AVW-003-07	6.38CPClR	32%	40%	4.6	0.52	0.61	1.83
AVW-003-08	6.38CPGy	25%	50%	4.6	0.38	0.29	1.83
AVW-003-09	8.76ESITOGn	24%	53%	4.5	0.35	0.51	1.83
AVW-003-10	10.38Sx	17%	28%	6.0	0.58	0.64	1.83
AVW-003-11	10.38EV	29%	45%	4.6	0.45	0.49	1.83
AVW-003-12	10.38CPClR	32%	43%	4.5	0.49	0.59	1.83

## Standard Aluminium Sashless in Capral 400 Frame – Double Glazed

Window ID	Glazing	Heat%	Cool %	Uw	SHGC	Tvw	Air Inf
AVW-004-01	4Clr/10Ar/4Clr	41%	37%	4.1	0.59	0.62	1.83
AVW-004-02	4Clr/10Ar/4ET	47%	42%	3.5	0.56	0.57	1.83
AVW-004-03	4ET/10Ar/4ET	45%	48%	3.4	0.49	0.53	1.83
AVW-004-04	4Clr/8Ar/6ET	45%	42%	3.6	0.55	0.56	1.83
AVW-004-05	4Clr/8Ar/6EV	42%	46%	3.7	0.50	0.48	1.83
AVW-004-06	6SpGy/6ClrAr/6Clr	17%	64%	4.3	0.19	0.06	1.83
AVW-004-07	6LoE366/6ClrAr/6Clr	28%	64%	3.6	0.24	0.48	1.83
AVW-004-08	6LoE366/6Ar/6ET	27%	65%	3.6	0.23	0.44	1.83
AVW-004-09	6Clr/6Ar/6ET	42%	43%	3.8	0.53	0.56	1.83
AVW-004-10	6Clr/6Ar/6Sn	39%	45%	3.9	0.50	0.46	1.83
AVW-004-11	4Clr/8Ar/6.38CPClR	45%	42%	3.6	0.55	0.57	1.83
AVW-004-13	4Gy/10Ar/4Clr	34%	48%	4.1	0.44	0.38	1.83
AVW-004-14	6Gy/8Ar/4Clr	29%	53%	4.2	0.37	0.29	1.83
AVW-004-15	4ET/10Ar/4Gy	43%	48%	3.5	0.48	0.36	1.83
AVW-004-16	LB ClrS0 4/10/4	44%	51%	3.3	0.46	0.61	1.83

Source: [awawers.net/comsearch/search/vic](http://awawers.net/comsearch/search/vic), filter 'Manufacturers' by 'Austview'.

## Standard Timber Sashless – Single Glazed

Window ID	Glazing	Heat%	Cool %	Uw	SHGC	Tvw	Air Inf
AVW-001-01	6Clr	34%	28%	4.9	0.64	0.68	1.83
AVW-001-02	6Gy	25%	44%	4.9	0.45	0.32	1.83
AVW-001-03	6SpGy	15%	55%	4.9	0.28	0.07	1.83
AVW-001-04	6EV	45%	48%	3.4	0.49	0.53	1.83
AVW-001-05	6ET	48%	45%	3.3	0.54	0.63	1.83
AVW-001-06	6.38Sx	33%	30%	4.9	0.62	0.68	1.83
AVW-001-07	6.38CPClr	49%	46%	3.2	0.53	0.63	1.83
AVW-001-08	6.38CPGy	40%	56%	3.3	0.39	0.30	1.83
AVW-001-09	8.76ESITOGn	40%	58%	3.2	0.36	0.53	1.83
AVW-001-10	10.38Sx	33%	33%	4.8	0.59	0.67	1.83
AVW-001-11	10.38EV	44%	51%	3.3	0.45	0.51	1.83
AVW-001-12	10.38CPClr	47%	48%	3.2	0.50	0.61	1.83

## Standard Timber Sashless – Double Glazed

Window ID	Glazing	Heat%	Cool %	Uw	SHGC	Tvw	Air Inf
AVW-002-01	4Clr/10Ar/4Clr	55%	42%	2.9	0.60	0.63	1.83
AVW-002-02	4Clr/10Ar/4ET	61%	48%	2.2	0.56	0.59	1.83
AVW-002-03	4ET/10Ar/4ET	59%	54%	2.1	0.49	0.54	1.83
AVW-002-04	4Clr/8Ar/6ET	59%	48%	2.4	0.55	0.58	1.83
AVW-002-05	4Clr/8Ar/6EV	56%	52%	2.4	0.50	0.49	1.83
AVW-002-06	6SpGy/6ClrAr/6Clr	30%	71%	3.1	0.18	0.06	1.83
AVW-002-07	6LoE366/6ClrAr/6Clr	41%	71%	2.4	0.23	0.49	1.83
AVW-002-08	6LoE366/6Ar/6ET	40%	71%	2.4	0.22	0.45	1.83
AVW-002-09	6Clr/6Ar/6ET	55%	49%	2.6	0.53	0.57	1.83
AVW-002-10	6Clr/6Ar/6Sn	53%	51%	2.7	0.50	0.47	1.83
AVW-002-11	4Clr/8Ar/6.38CPClr	60%	49%	2.3	0.55	0.58	1.83
AVW-002-13	4Gy/10Ar/4Clr	48%	54%	2.9	0.44	0.39	1.83
AVW-002-14	6Gy/8Ar/4Clr	43%	58%	3.0	0.37	0.29	1.83
AVW-002-15	4ET/10Ar/4Gy	57%	55%	2.2	0.48	0.36	1.83
AVW-002-16	LB ClrS0 4/10/4	58%	57%	2.0	0.46	0.62	1.83

Source: [awawers.net/comsearch/search/vic](http://awawers.net/comsearch/search/vic), filter 'Manufacturers' by 'Austview'.